



Roopal PV 19

Technical Data Sheet

Properties	Value/ Description	
Color Index	Pigment Violet 19 Gamma yellowish	
C.I. No.	73900	
Chemical Formula	C ₂₀ H ₁₂ N ₂ O ₂	
CAS#	1047-16-1	
Physical Form	Violet Powder	
Heat Resistance*^oC	300	
Density (g/cm³)	1.5	
Specific Surface (m²/g)	52	
pH Value	6.0 to 7.0	
Oil Absorption (ml/100gm)	68	
Fastness Properties	Full Color	Tint Color
Dispersibility	Excellent	Excellent
Light Fastness	8	7-8
Acid Resistance	5	4-5
Alkali Resistance	5	4-5
Weather Resistance	5	4-5
Water Resistance	5	4-5
Oil Resistance	5	4-5

Key features:

- **Printing Inks:** Water based, Solvent based, UV and Inkjet inks
- **Coatings:** Architectural, Coil & Powder Coatings, Industrial & Automotive Paints.

Disclaimer: Users should use this information, only as a supplement to other information gathered by them, and should make their own independent judgement of suitability of this information to ensure proper use while protecting health & safety of employees/users. We recommend thorough testing in the lab for its suitability before its use in the production. We make no warranty whether expressed or implied, including warranties of merchantability or fitness for particular purpose. Neither do we assume any responsibility for infringement of third parties patent rights which may arise from the use of this product.